

Bauder Quick Dry Bitumen Primer - Black

V3 17.11.2022

Product description	Bauder Quick Dry Primer is a bitumen-based primer applied by a roller or brush. 'Quick Dry' is in comparison to standard bitumen primers.
Application fields	Bauder Quick Dry Bitumen Primer is specially formulated to increase the bond strength of Bauder torch-on bitumen membranes and Bauder Hot Melt waterproofing to a wide range of substrates, including, concrete, brick, & metal.
Article Number	GB60250110



Characteristic	Unit	Value
Pack size	litre	25
Colour		Black
Base		Bitumen
Coverage (depending on substrate porosity)	litres/m ²	4 to 8
Temperature resistance	°C	≤ 60
Viscosity	CPS	800 to 1000 @20°C
Shelf life unopened	months	12
Application Temperature	°C	+5 to +25 (Where the temperature falls outside of this, please refer to Summer & Winter Advice documents from Bauder).
Drying time	hours	3 to 6 depending on porosity and weather conditions
Cleaner		Bauder PMMA Cleaner
Re-coat time if left exposed	hours	4

Storage guidance	The product should be stored in a secure storage cage, unopened in a dry condition at a temperature of 5°C to 25°C. This will ensure the stated shelf-life. The product will have a limited life once the container is opened.
Packaging material	The product will be delivered in a steel drum (readily recyclable).
Handling/PPE	All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using the product, installers should be provided with, and wear, suitable personal protective equipment.
Emptying and disposal guidance	Containers which have been emptied, but not washed out in line with the specific methods and calculations prescribed in WP1 and WM3, should be classified as packaging containing residues of/ or contaminated by hazardous substances using waste code 15-01-10. Containers with hazardous residues that have been emptied and washed-out in line with the method and calculations which are detailed in the industry guidance can be classified as non-hazardous waste packaging.
Further information/ documents	Current documents such as brochures, installation guides, etc. can be found by visiting www.bauder.co.uk

International Standards Organisation (ISO)

ISO 9001:2015 Quality Management
Certificates EN1271 (UK)

ISO 14001:2015 Environmental Management Certificates
A10552 (UK)

Technical data sheet



Installation Guidance

1. Surfaces must be clean, dry and free from contamination.
2. Ambient application temperature must be between +5 and +25°C.
3. Stir thoroughly before use.
4. Apply by brush or roller at a rate of 4 to 8 m² per litre depending on substrate porosity.
5. Avoid pooling as this will be difficult to spread and will increase drying time.
6. A second coat may be required (once the first is dry) on very porous substrates.
7. Avoid trafficking after application.
8. Do not apply membranes before the primer is thoroughly dry and never within 3 hours of application.
9. Part used containers can be stored for future use, providing they are properly re-sealed.
10. Tools can be cleaned using Bauder PMMA cleaner.

Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as a substance/mixture; therefore, this product does have a requirement for a Safety Data Sheet.