Technical data sheet BauderTEC Sprint DUO Roofing membrane



23/02/2023

Product description	sealing. T lap there	er bitumen self-adhesive underlayer with variable technology for lap The two side laps of the membrane have differing finishes. On one is a self-adhesive finish, whist the opposite lap has a glass fleece. vs the membrane to be sealed with either a gas torch or hot air	
Application fields	-	er in a flat roof system. Can be used adhered on a variety of tely prepared substrates and insulants.	A STATE OF THE STA
Surface	top:	PE foil	
	bottom:	release film (cold self-adhesive bitumen underside)	
Reinforcement type and weight	glass latti	ice with glass fleece combination	
Article number	1625 000	0	
abP	P-51-10-0049		

Characteristic	Test method	Unit	Value
Length	EN 1848-1	m	15
Width	EN 1848-1	m	1
Thickness	EN 1849-1	mm	2
Mass per unit area	-	kg/m²	2,5
Straightness	EN 1848-1	mm/10m	<20
Reaction to fire	EN 13501-1	-	E
Watertightness	EN 1928	-	passed
Flexibility at low temperature top	EN 1109	°C	≤-30
Flexibility at low temperature bottom	EN 1109	°C	≤-30
Flow resistance at elevated temperature top	EN 1110	°C	≥100
Flow resistance at elevated temperature bottom	EN 1110	°C	≥100
Max. tensile force length	EN 12311-1	N/50mm	≥1000
Max. tensile force transverse	EN 12311-1	N/50mm	≥1000
Elongation at max. tensile force length	EN 12311-1	%	≥2
Elongation at max. tensile force transverse	EN 12311-1	%	≥2

CE(06)

Notified body: GPB, 1724 EN 13707



Notified body: BBA 0836 BS EN 13707

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH T: +44 (0)1473 257671 - E: info@bauder.co.uk www.bauder.co.uk

Bauder reserves the right to update this data set without prior notice and this document is uncontrolled if printed or stored. Always confirm the latest version is used for the adoption of this product, available from our website: bauder.co.uk/technical-centre. Intended use of this product should be verified with Bauder to ensure suitability and compliance

with applicable guidance, regulations, legislations, project requirements, specifications, and installation techniques.

Technical data sheet BauderTEC Sprint DUO Roofing membrane



Characteristic	Test method	Unit	Value			
External fire performance	CEN/TS 1187	-	Product has been fire tested as part of a system assembly and this information can be obtained in the Fire Test Report available from Bauder Ltd.			
Product surface finish	If the laps of the membrane are heat sealed, the membrane can be used as temporary waterproofing. A temporary waterproofing is a temporary protection against rain. It is part of the concept of a temporary waterproofing, and this must be monitored during the construction phase and, inspected for damage prior to installation of the rest of the waterproofing system. If the membrane is left exposed after a maximum period of 2 months, the membrane should be covered by the additional waterproofing system. It must also be clear that the criteria of a permanent waterproofing cannot be expected from this temporary waterproofing application.					
Product storage guidance	On end/Upright - The membranes must also be protected from UV rays, moisture and heat.					
Pallet size	Pallet size =20 rolls/300m ² per pallet					
Storage temperature range	+5°C to +30°C					
Packaging material	The product will be delivered on wooden pallets with plastic overwrap to protect the product. Each roll has a paper wrapping/tape to the external of the product, which must be removed before use.					
Handling/PPE	All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using/handling the product, installers should be provided with, and wear, suitable personal protective equipment.					
Shelf life	When stored correctly, the product has a stated shelf life of 9 months. We would suggest additional installation techniques may be required to ensure adequate adhesion is achieved.					
Disposal guidance		Bitumen waste can be disposed of with household waste or commercial waste similar to household waste (European waste catalogue EWC number 170302 "asphalt tar-free").				
Re-use options of product	Please refer	Please refer to EPD stated below in Certification and environmental information.				
Further information/documents		Current documents such as DoC's, DoP's (where relevant), brochures, installation guides, etc. can be found by visiting www.bauder.co.uk				
Certification and environmental information	BBA Certifi 10/4744	cate No.:				
		ntal Product Declara IntEPD S-P-00768	tion:			
	ISO 9001:20	International Standards Organisation (ISO): ISO 9001:2015 Quality Management Certificates EN1271 (UK) and 70499/03-15_e (Germany)				
		2015 Environmental M A10552 (UK) and 704	1anagement 199/03-15_d (Germany)			
		2011 Energy Manage 0499/03-15_c (Germa				
Safety Data Sheet	Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as an article; therefore, this product does not have a requirement for a Safety Data Sheet.					

CE(06)

Notified body: GPB, 1724 EN 13707



Notified body: BBA 0836 BS EN 13707

UNITED KINGDOM Bauder Ltd 70 Landseer Road, Ipswich, Suffolk IP3 0DH T: +44 (0)1473 257671 - E: info@bauder.co.uk www.bauder.co.uk

Bauder reserves the right to update this data set without prior notice and this document is uncontrolled if printed or stored. Always confirm the latest version is used for the adoption of this product, available from our website: bauder.co.uk/technical-centre. Intended use of this product should be verified with Bauder to ensure suitability and compliance

with applicable guidance, regulations, legislations, project requirements, specifications, and installation techniques.