

Technical data sheet

BauderPIR T KL 50

Angle Fillets



22/11/2022

Product description	BauderPIR angle fillets are a triangular profiled section of BauderPIR insulation. The product is un-faced and requires priming and gluing prior to application of Bauder underlayers.		
Application fields	For use in conjunction with BauderPIR Insulation. Can also be used in cold roof scenarios. The product is designed to fully support the waterproof membrane at 90° abutments, providing a smooth transition between the horizontal and vertical interface.		
Article number	9610 7050		
Facing	top:	None	
	bottom:	None	
Cutting	Fillets can be cut with a fine-toothed saw or straight bladed craft knife.		
Description	PU-EN13165-T2-DS(70,90)3-DS(-20,-)2-CS(10Y)120-TR100		

Characteristic	Test method	Unit	Value
Length	EN 822	mm	1000
Width 1 (height when installed)	EN 822	mm	50
Width 2 (height when installed)	EN 822	mm	50
Diagonal	-	mm	70
Thickness	EN 823	mm	35
Thermal conductivity (λ_D) - (EU)	EN 13165	W/mK	0,026
Water absorption	EN 12087	Vol%	max. 3
PIR Index	-	-	>250

Installation guidance

- BauderPIR angle fillets must be installed in dry conditions
- With the longest face facing outward, place the angle fillet against the upstand, bonded in the specified Bauder adhesive
- Prime the face of the angle fillet with Activator-Primer prior to installation of the Bauder underlayer
- Adjacent lengths of angle fillet to be closely butted together
- BauderPIR angle fillets can be cut to size using a fine-toothed saw

Product storage guidance

Thermal insulation has to be transported and stored protected from moisture, open flames and direct sunlight. All insulation boards must be kept dry, on pallets and off the ground. The packaging of Bauder Insulation products should not be considered adequate for outside protection. Ideally boards should be stored inside a building. If outside storage cannot be avoided the boards should be stacked clear of the ground and covered with an opaque polythene sheet or weatherproof tarpaulin. Store under cover. Angle fillets that have become wet must be allowed to fully dry out naturally before use.

Packaging material

The product will be delivered in a cardboard box (readily recyclable) containing 288 linear metres of angle fillets.

Handling/PPE

All persons using the product should be fully aware of the manual handling methods as roofing materials are heavy and can cause serious injury. When using the product, installers should be provided with, and wear,



Notified body: FIW München, 0751
EN 13165



Technical data sheet

BauderPIR T KL 50

Angle Fillets



	suitable personal protective equipment.
Shelf life	When stored correctly, the product has no stated shelf life.
Disposal guidance	Rigid polyurethane foam waste can be disposed of with household waste or commercial waste similar to household waste (European waste catalogue EWC number 170604 "Insulation material").
Further information/documents	Current documents such as DoC's, DoP's (where relevant), brochures, installation guides, etc. can be found by visiting www.bauder.co.uk
Certification and environmental information	International Standards Organisation (ISO): ISO 9001:2015 Quality Management Certificates EN1271 (UK) and 70499/03-15_e (Germany) ISO 14001:2015 Environmental Management Certificates A10552 (UK) and 70499/03-15_d (Germany) ISO 50001: 2011 Energy Management Certificate 70499/03-15_c (Germany)
Safety Data Sheet	Safety Data Sheets are designed to provide the necessary information to recipients of substances and mixtures in the EU & UK. This product is classed as an article; therefore, this product does not have a requirement for a Safety Data Sheet.



Notified body: FIW München, 0751
EN 13165

